

SOLIDFLOW SL 2000

SOLVENT FREE 2-3MM SELF SMOOTHING EPOXY FLOOR SYSTEM

DESCRIPTION

SOLIDFLOW SL 2000 is a three component, solvent-free, self-leveling epoxy system applied at a nominal thickness of 2mm. SOLIDFLOW SL 2000 exhibits superior abrasion and chemical resistance on concrete floors and creates a hygienic, smooth finish ideal for dry process areas in the food, beverage and pharmaceutical industries.



TECHNICAL DETAILS

Application:	Self-leveling
Profile:	Smooth
Finish:	Gloss
Colours:	Various
Application Temp:	12-30°C
Service Temp:	60°C max (dry)
Dry film thickness:	2mm system
Solids content:	100%
Touch Dry:	10 - 12 hours
Hard Dry:	24 hours
Full Cure:	7 days
Pot-life:	30 min @ 20°C
Yield:	24L
Coverages:	12 m ² per Kit @ 2mm 8 m ² per kit @ 3mm
Compressive strength:	> 55M/mm ² (BS 6319)
Flexural strength:	> 30 N/mm ² (BS 6319)
Bond strength:	> 1.5 MPa
Tensile strength:	> 15 MPa
Toxicity:	Taint free to sensitive food consumables

ADVANTAGES

- Seamless finish
- Easy to clean and maintain
- Excellent chemical resistance
- Hard wearing floor finish
- Excellent abrasion resistance
- Non-dusting
- Rapid installation

APPLICATIONS

- Factory and warehouse floors
- Laboratories
- Electronic (Clean rooms)
- Automotive
- Aerospace (Hangars)
- Medium to heavy duty traffic environments where durability is required

SUBSTRATE REQUIREMENTS

- Substrate screeds are recommended to be Grade 2 concrete or of 20MPa compressive strength or higher with minimum pull off strength of 1.5 N/mm²
- All surfaces to be suitably prepared using grinders, shot blasting or scarifiers to remove laitance
- Substrate screeds must be clean and free of oily residues and friable material
- The substrate should be dry to 75% RH (BS 8204) and free from rising damp or ground water pressure.
- Porous substrate screeds must be sealed with a primer such as SOLIDKOTE UP Epoxy Primer, SOLIDKOTE 405, SOLIDKOTE ROBUST CLEAR (See Datasheets)

SYSTEM DETAILS

SOLIDKOTE UP PRIMER and SOLIDFLOW SL 2000

PACKAGING

SOLIDFLOW SL 2000 is supplied in pre-packed kits consisting of three parts including Part A (resin), Part B (Activator) and Part C (Powder) producing a total yield of 24L per kit.

DIRECTIONS

Prime the area with a suitable primer (Solidkote UP Epoxy Primer) and allow curing for not more than 18 hours before proceeding with the SOLIDFLOW SL 2000 system. The primer must provide a visibly complete seal on top of the floor surface or apply another coat of primer. Broadcast scatter sand (Sand # 12) into the wet primer if time before top-coat application will exceed 18 hours.

Add the complete contents of the PART B container to that of the PART A container and mix well to a uniform colour using a mechanical mixing device such as a Festo or pan mixer. Then slowly add the PART C (powder) to the mix and mix very well for at least three minutes. Pour this mix onto the floor, do not retain any of the mix in the mixing container as it will start to cure rapidly. Spread the mix using a 4mm notched trowel or rake for a 2mm finish or a 6mm notched rake for a 3mm finish then smooth off with the flat edge of the trowel. Allow to self-degas for 3minutes and then spike roll the surface to remove any entrapped air.

Spike roll again at 5-8 min to ensure sufficient removal of bubbles. Spike rolling should be done thoroughly to ensure that no more air bubbles are rising to the surface. Once satisfied that spike rolling is complete, it should be left to settle and not spike rolled again as this could lead to slight colour variations in areas treated differently. Alternatively the entire area will need to be spike rolled again to keep a consistent colour throughout. The screed will smooth out and should be protected from dust or other airborne contamination settling on the surface during the curing period.

SOLIDFLOW SL 2000 is a specialized system that must be installed by an approved applicator with documented quality assurance. Consult Technical Finishes for list of approved applicators.

HEALTH SAFETY

The system is non-hazardous to health and environment. Please consult Health and Safety Datasheets for each product from the Technical department or Representative.

Technical Finishes products are guaranteed against defective materials and are manufactured under high quality standards and are sold subject to its standard Terms and Conditions of sale, copies of which can be obtained on request.

Gauteng

35 Activia Rd, Activia Park, Germiston, 1610
Tel: +27 (0) 11 822 7242



Kwa-Zulu Natal

5 Progress Rd, New Germany, 3610
Tel: +27 (0) 31 705 7733

Western Cape

Cnr. Gunners Circle & Fisher Ave, Epping 1, 7475
Tel: +27 (0) 21 535 4455

